



# UNITED STATES PATENT AND TRADEMARK OFFICE

UNITED STATES DEPARTMENT OF COMMERCE  
United States Patent and Trademark Office  
Address: COMMISSIONER FOR PATENTS  
P.O. Box 1450  
Alexandria, Virginia 22313-1450  
www.uspto.gov

APPLICATION NO.	FILING DATE	FIRST NAMED INVENTOR	ATTORNEY DOCKET NO.	CONFIRMATION NO.
-----------------	-------------	----------------------	---------------------	------------------

10/575,262

04/10/2006

Fumiki Murakami

0152-0730PUS1

8789

2292 7590 09/10/2010  
BIRCH STEWART KOLASCH & BIRCH  
PO BOX 747  
FALLS CHURCH, VA 22040-0747

EXAMINER

NGUYEN, HAIDUNG D

ART UNIT

PAPER NUMBER

1796

NOTIFICATION DATE

DELIVERY MODE

09/10/2010

ELECTRONIC

**Please find below and/or attached an Office communication concerning this application or proceeding.**

The time period for reply, if any, is set in the attached communication.

Notice of the Office communication was sent electronically on above-indicated "Notification Date" to the following e-mail address(es):

mailroom@bskb.com

<b>Office Action Summary</b>	<b>Application No.</b> 10/575,262	<b>Applicant(s)</b> MURAKAMI, FUMIKI	
	<b>Examiner</b> Haidung D. Nguyen	<b>Art Unit</b> 1796	

-- The MAILING DATE of this communication appears on the cover sheet with the correspondence address --

#### Period for Reply

A SHORTENED STATUTORY PERIOD FOR REPLY IS SET TO EXPIRE 3 MONTH(S) OR THIRTY (30) DAYS, WHICHEVER IS LONGER, FROM THE MAILING DATE OF THIS COMMUNICATION.

- Extensions of time may be available under the provisions of 37 CFR 1.136(a). In no event, however, may a reply be timely filed after SIX (6) MONTHS from the mailing date of this communication.
- If NO period for reply is specified above, the maximum statutory period will apply and will expire SIX (6) MONTHS from the mailing date of this communication.
- Failure to reply within the set or extended period for reply will, by statute, cause the application to become ABANDONED (35 U.S.C. § 133). Any reply received by the Office later than three months after the mailing date of this communication, even if timely filed, may reduce any earned patent term adjustment. See 37 CFR 1.704(b).

#### Status

- 1) ☒ Responsive to communication(s) filed on 30 June 2010.
- 2a) ☒ This action is **FINAL**.                      2b) ☐ This action is non-final.
- 3) ☐ Since this application is in condition for allowance except for formal matters, prosecution as to the merits is closed in accordance with the practice under *Ex parte Quayle*, 1935 C.D. 11, 453 O.G. 213.

#### Disposition of Claims

- 4) ☒ Claim(s) 1 and 3-24 is/are pending in the application.
- 4a) Of the above claim(s) \_\_\_\_\_ is/are withdrawn from consideration.
- 5) ☐ Claim(s) \_\_\_\_\_ is/are allowed.
- 6) ☒ Claim(s) 1, 3-24 is/are rejected.
- 7) ☐ Claim(s) \_\_\_\_\_ is/are objected to.
- 8) ☐ Claim(s) \_\_\_\_\_ are subject to restriction and/or election requirement.

#### Application Papers

- 9) ☐ The specification is objected to by the Examiner.
- 10) ☐ The drawing(s) filed on \_\_\_\_\_ is/are: a) ☐ accepted or b) ☐ objected to by the Examiner.  
Applicant may not request that any objection to the drawing(s) be held in abeyance. See 37 CFR 1.85(a).  
Replacement drawing sheet(s) including the correction is required if the drawing(s) is objected to. See 37 CFR 1.121(d).
- 11) ☐ The oath or declaration is objected to by the Examiner. Note the attached Office Action or form PTO-152.

#### Priority under 35 U.S.C. § 119

- 12) ☐ Acknowledgment is made of a claim for foreign priority under 35 U.S.C. § 119(a)-(d) or (f).
- a) ☐ All    b) ☐ Some \*    c) ☐ None of:
1. ☐ Certified copies of the priority documents have been received.
2. ☐ Certified copies of the priority documents have been received in Application No. \_\_\_\_\_.
3. ☐ Copies of the certified copies of the priority documents have been received in this National Stage application from the International Bureau (PCT Rule 17.2(a)).

\* See the attached detailed Office action for a list of the certified copies not received.

#### Attachment(s)

- |   |   |
|---|---|
| 1) <input type="checkbox"/> Notice of References Cited (PTO-892)                    | 4) <input type="checkbox"/> Interview Summary (PTO-413)           |
| 2) <input type="checkbox"/> Notice of Draftperson's Patent Drawing Review (PTO-948) | Paper No(s)/Mail Date. _____                                      |
| 3) <input type="checkbox"/> Information Disclosure Statement(s) (PTO/SB/08)         | 5) <input type="checkbox"/> Notice of Informal Patent Application |
| Paper No(s)/Mail Date _____   | 6) <input type="checkbox"/> Other: _____                          |


### DETAILED ACTION

1. This action is responsive to applicant's amendment filed 6/30/2010.
2. Claims 1, 3-24 are currently pending.

#### ***Claim Rejections - 35 USC § 103***

3. Claims 1, 3-24 are rejected under 35 U.S.C. 103(a) as being unpatentable over Taniguchi et al (WO01/070844). U.S. 2003/0114606, which is the U.S. Nation Stage of the Taniguchi reference, is used as translation.

Regarding claims 1, 3, 4, Taniguchi discloses a flame retardant composition which comprises: (A) at least one compound selected from the group consisting of (A-1) a metal oxide (aluminum oxide, zinc oxide, para 0091, ln 7-9) and (A-2) a trivalent phosphorus compound (triphenyl phosphine – para 0104, ln 32); and (B) at least one phosphazene containing 80% by weight or more of cyclic trimers (synthesis examples 2, 4 and 5) selected from a group consisting of a cyclic and a chain phosphazene compound represented by formula (1) corresponding to applicant's formulas (2) and (3) and , wherein the flame retardant composition contains 0.1-60 parts by weight of the component (A) (para 0100, ln 1-16; Table 1, triphenylphosphine) and 99.9-40 parts by weight of the component (B) in 100 parts by weight of the component (A) and the component (B) in total (para 0100, ln 1-16).



Formula (1)

Art Unit: 1796

Taniguchi does not disclose the metal oxide being selected from the group consisting of iron oxide, nickel oxide, palladium oxide and copper oxide. However, Nakacho discloses the flame retardant composition comprises metal oxide selected from the group consisting of iron oxide, nickel oxide, palladium oxide and copper oxide (Nakacho, col 11, ln 60-61).

It would have been obvious to one of ordinary skill in the art at the time the invention was made to substitute iron oxide, nickel oxide, palladium oxide and copper oxide taught by Nakacho in place of zinc oxide in the flame retardant composition of Taniguchi to obtain predictable result, since Nakacho recognizes that zinc oxide and iron oxide and copper oxide are equivalent and interchangeable (Nakacho, col 11, ln 60-61).

Taniguchi does not disclose the phosphazene compound having a difference of 40-100°C between the temperature at which weight reduction is 50% by weight and the temperature at which the weight reduction is 5% by weight when it is heated from room temperature to 600°C at a heating rate of 10°C/min in an inert gas atmosphere according to TGA, an acid value of not more than 1.0, a water content of not more than 1000 ppm measured at 150°C according to Karl Fischer's method, and the temperature at which the weight reduction of the phosphazene compound is 50% by weight is 320-460°C when it is heated from room temperature to 600°C at a heating rate of 10°C/min in an inert gas atmosphere according to TGA. However, since the phosphazene compound and the flame retardant composition of Taniguchi is identical that set forth by applicant; thus, the phosphazene compound and the flame retardant of Taniguchi would

Art Unit: 1796

inherently possess the same properties as claimed. "Product of identical chemical composition can not have mutually exclusive properties". A chemical composition and its properties are inseparable. "Where the claimed and prior art products are identical or substantially identical in structure or composition, a prima facie case of either anticipation or obviousness has been established." *In re Best*, 562 F.2d 1252, 1255, 195 USPQ 430, 433 (CCPA 1977). "When the PTO shows a sound basis for believing that the products of the applicant and the prior art are the same, the applicant has the burden of showing that they are not." *In re Spada*, 911 F.2d 705, 709, 15 USPQ2d 1655, 1658 (Fed. Cir. 1990).

Regarding claims 7-9, Taniguchi discloses the flame retardant composition according to claim 1, the component (A-2) is triarylphosphines (Taniguchi triphenyl phosphine – para 0104, ln 32).

Regarding claims 10-14, Taniguchi discloses the flame retardant composition according to claim 1 which further comprises (C) an aromatic resin, wherein the component (C) is polyphenylene ether resin (Taniguchi para 0109, ln 21) and the weight ratio of the component (C) and the component (B) is  $(C)/(B) = 95/5 - 5/95$  (Taniguchi para 0109, ln 48-50).

Regarding claims 15 and 16, Taniguchi discloses a flame retardant resin composition which contains (a) a resin and (b) the flame retardant composition described in claim 1, which contains 1-1000 parts by weight of the component (b) based on 100 parts by weight of the component (a) (Taniguchi para 0109, ln 48-50).

Art Unit: 1796

Regarding claims 17-19, Taniguchi discloses the flame retardant resin composition according to claim 15, wherein the component (a) comprises at least one thermoplastic resin selected from the group consisting of polycarbonate resins, polyphenylene ether resins, polyphenylene sulfide resins, polypropylene resins, polyethylene resins, polystyrene resins, ABS resins, polyalkylene terephthalate resins, polyamide resins, thermotropic liquid crystals and elastomer-containing polystyrenes (Taniguchi para 0109).

Regarding claims 20 - 22, Taniguchi discloses the flame retardant resin composition according to claim 15, wherein the component (a) comprises at least one hardening resin selected from the group consisting of unsaturated polyester resins, vinyl ester resins, diallyl phthalate resins, epoxy resins, cyanate resins, xylene resins, triazine resins, phenolic resins, urea resins, melamine resins, benzoguanamine resins, urethane resins, ketone resins, alkyd resins, furan resins, oxetane resins, styrylpyridine resins and synthetic rubbers (Taniguchi, epoxy para 0022-0023 and 0109)

Regarding claim 23, Taniguchi discloses the flame retardant resin composition according to claim 15 or 16, further comprises (C) an aromatic resin which is a polyphenylene ether resin (Taniguchi para 0109, ln 21). Taniguchi does not disclose the polyphenylene ether resin having a number average molecular weight of 500-5000. However, it would have been obvious to one of ordinary skill in the art at the time the invention was made to select the polyphenylene ether resin having a number average molecular weight within the claimed range because one of ordinary skill would be able

to carry out such selection depending on the end use and the results are reasonably predictable.

Regarding claim 24, Taniguchi discloses a molded article comprising the flame retardant resin composition according to claim 14 (Taniguchi, para 0111, ln 9).

### ***Response to Arguments***

4. Applicant's arguments with respect to Nakacho et al have been fully considered and are persuasive. Thus, the rejection has been withdrawn.

5. Applicant's arguments with respect to Taniguchi et al have been fully considered but they are not persuasive.

Applicant argues that a person skilled in the art would not be motivated to use any phosphazene compound having no heteroatom containing group as recited in the instant claim 1 to prepare a flame retardant composition based on the teachings of Taniguchi. However, a person skilled in the art would not need a motivation to arrive at the claimed formula based on the teachings of Taniguchi because Taniguchi teaches phosphazene compound of formula (1) which clearly reads on the claimed formulas, especially when the claimed formula having substituents X are alkoxy group of 1-6 carbon atoms.

Applicant further argues that Taniguchi does not disclose, teach or suggest using combination of the phosphazene compound and a specific kind of a metal oxide or a trivalent phosphorous compound at a specific ratio. The examiner is noted, however, there is no specific ratio of any two specific components is being claimed. Taniguchi

Art Unit: 1796

teaches a flame retardant composition contains 0.1-60 parts by weight of the component (A) at least one compound selected from the group consisting of (A-1) a metal oxide (aluminum oxide, zinc oxide, para 0091, ln 7-9) and (A-2) a trivalent phosphorus compound (triphenyl phosphine – para 0104, ln 32); (para 0100, ln 1-16; Table 1, triphenylphosphine) and 99.9-40 parts by weight of the phosphazene component (B) in 100 parts by weight of the component (A) and the component (B) in total (para 0100, ln 1-16 and Table 1), which meet the claimed limitations as recited in instant claim 1.

#### ***Examiner Information***

Any inquiry concerning this communication or earlier communications from the examiner should be directed to Haidung D. Nguyen whose telephone number is (571)270-5455. The examiner can normally be reached on M-Th: 9:00am-5:00pm.

If attempts to reach the examiner by telephone are unsuccessful, the examiner's supervisor, Harold Pyon can be reached on 571-272-1498. The fax phone number for the organization where this application or proceeding is assigned is 571-273-8300.



Art Unit: 1796

Information regarding the status of an application may be obtained from the Patent Application Information Retrieval (PAIR) system. Status information for published applications may be obtained from either Private PAIR or Public PAIR. Status information for unpublished applications is available through Private PAIR only. For more information about the PAIR system, see <http://pair-direct.uspto.gov>. Should you have questions on access to the Private PAIR system, contact the Electronic Business Center (EBC) at 866-217-9197 (toll-free). If you would like assistance from a USPTO Customer Service Representative or access to the automated information system, call 800-786-9199 (IN USA OR CANADA) or 571-272-1000.

/Harold Y Pyon/  
Supervisory Patent Examiner, Art Unit 1796

/Haidung D Nguyen/

Examiner, Art Unit 1796